

Stukko Fix Szerelési Ragasztó Tytan Professional

Egykomponensű, vizes diszperziós bázisú rögzítő ragasztó, polisztirol és poliuretán hab elemek nedvszívó felületekre történő ragasztására ajánlott, mint például beton, gipsz forgácslap, fa, gipszkarton, gipsz.

Alkalmazás

- polisztirolból és poliuretánhabból készült hő- és hangszigetelő anyagok ragasztása
- ásványgyapot és üveggyapot ragasztása
- szegélylécek, padlólapok, deszkák és dekoratív hungarocell elemek ragasztása

Előnyök

- kikeményedés után fehér kötést képez
- oldószer-mentes
- semleges szag
- nem gyúlékony
- rugalmas csatlakozás

Felhasználási mód

Alkalmazás előtt olvassa el az MSDS-ben található biztonsági utasításokat.

1 Termék Előkészítés

- Vágja le a kinyomócsőrt a kívánt átmérőre, vágja le a kartus kimenetét és csavarja rá a kinyomócsőrt. Helyezze be a kartust a kinyomó pisztolyba.

2 Felület Előkészítés

- A ragasztott felületeknek szilárdnak, száraznak, szennyeződéstől és a tapadást akadályozó anyagoktól mentesnek kell lenniük.

3 Application

- Apply adhesive in spots or strips on the surface or bonded material.
- Apply the adhesive on surface which can be glued within 10 - 15 minutes.
- Next match bonded surfaces and press.

4 Works After Completion Of Application

- Cleaning: water before curing, mechanically after curing.
- DO NOT WASH HANDS WITH SOLVENTS.

5 Remarks / Restriction

- At least one surface must be absorbent.
- Adhesion tests prior to application of the adhesive are recommended.
- Avoid contact with water until the adhesive is fully cured.
- Not suitable for PE, PP, Teflon and bituminous surfaces.

Technical Data

Uncured	Value
Base: acrylic dispersion	+
Solid Content [%]	72 - 78
Density [g/cm ³]	1,4 - 1,5
Working time (depending on ambient conditions and subfloor properties) [min]	10 - 15
Flammability	-
Full cure time [h]	48
Consumption [g/m ²]	200 - 400
Cured	Value
Temperature resistance [°C]	-20 - +60
Conditions of application	Value
Application temperature [°C]	+10 - +30
Colour	Value
White	+

Transport / Storage

Warranted shelf life is 24 months from the manufacturing date when stored in unopened, original package at temperatures from +5 °C to +30 °C in a dry place protected from freezing and excessive heat.

Safety And Health Precautions

For detailed information find Material Safety Data Sheet available at producer upon request. Disposal considerations: Product remains and empty cartridges must be disposed of in compliance with official, local regulations.

All written or oral information, recommendations and instructions are given according to our best knowledge, tests and experience, in good faith and in compliance with manufacturer's principles. Each user of this material will make sure in every possible way, including verification of the final product in proper conditions, about suitability of the supplied materials for their intended purposes. The manufacturer is not liable for any losses incurred due to inaccurate or erroneous application of the manufacturer's materials.